

REPORT ON SUBMITTED SAMPLE RECEIVED ON 26 November 2004

Sample Description: ¾" Netting

Test(s) requested: BS 5867-Type B

Test results:

Date(s) of test Tested between 26/11/04 and 30/11/04

Specification for curtains and drapes (BS 5867: Part 2: 1980)

Flammability requirements: Type B performance

Cleansing procedure: The fabric was tested in the "as received" condition.

Requirements: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen, and there shall be no separation of flaming debris.


Conditioning: The samples were conditioned in an atmosphere having a temperature of 20±2°C and a relative humidity of 55% to 65%.

Results: These results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

<u>Flame application time : 15 s</u>	Length			Width		
	1	2	3	1	2	3
Afterflame (s)	0	0	0	0	0	0
Afterglow (s)	0	0	0	0	0	0
Flame reached an edge :	No	No	No	No	No	No
Hole reached an edge :	No	No	No	No	No	No
Flaming debris :	No	No	No	No	No	No



Comments: The sample tested meets the requirements of BS 5867: Part 2: 1980 Type B performance.



Paula Smith
 Textile Technologist, Softlines Department

All orders are accepted and all services are rendered subject to the General Conditions of Service available upon request and accessible at www.sgs.com.
 Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein.